

# GTS-PP-65

## 3LPP Hybrid Coating System

The GTS-PP-65 system is a hybrid system combining a Polypropylene backing with a mastic adhesive. This combination results in a product with the mechanical protection of polypropylene with the ease of installation of a traditional adhesive. This also allows for a lower preheat temperature and faster application than found with traditional 3LPP systems.

### Superior Mechanical Protection

- The GTS-PP-65 sleeve has superior impact and shear resistance by virtue of its polypropylene backing. The sleeve is engineered for use in offshore applications where mechanical resistance is required and the rapid cooling of polypropylene allows better resistance to offshore laying rollers.

### Unique Adhesive Technology

- Allows for lower installation pre-heat temperatures and superior bonding to PP, PE, FBE, AE and CTE coatings.
- The adhesive has been formulated to bond directly to the steel and mainline coating.

### Flexible installation

- For added flexibility, the sleeve can be supplied as either pre-cut to the required pipe sizes or as bulk rolls.

### Long Term Corrosion Protection

- Provides a protective coating with the structural integrity of a seamless tube, providing excellent resistance to cathodic disbondment and excellent durability against abrasion and chemical attack.

### Saves time and Money

- Lower pre-heat means less time heating and a faster installation.
- Excellent quenching properties allow for faster cycle times during offshore installations.



### Applications



Oil & Gas



Offshore, J & S Lay



High Abrasion Environments



High Moisture Environments



# GTS-PP-65

## 3LPP Hybrid Coating System

Sleeve Operating Characteristics	Test Method	Typical Values	
Offshore Pipeline Operating Temp.		Up to 65°C (149°F)*	
Minimum Installation Temp.		75°C (167°F)	
Rapid Quenching Ability		Excellent	
Main Line Coating Compatibility		PE, PP, FBE, AE & CTE	
Adhesive Properties			
Softening Point	ASTM E28	102°C	
Lap Shear @ 23°C	EN 12068	40 N/cm <sup>2</sup>	
Backing Properties			
Tensile Strength	ASTM D638	28 MPa	
Elongation	ASTM D638	425%	
Hardness	ASTM D2240	65 Shore D	
Volume Resistivity	ASTM D257	2 x 10 <sup>17</sup> ohm-cm	
Sleeve Properties			
Adhesion Strength @ 23°C	EN 12068	8 N/cm	
Impact Resistance	EN 12068	> 20 J	
Indentation Resistance	EN 12068	Pass	
Cathodic Disbondment @ 23°C, 28 days	ASTM G8	< 8 mm rad	
Bending Resistance	GBE/CW6	Pass	
Thickness	T	L	S
Backing (nominal thickness as supplied)	0.6 mm (0.025")	0.9 mm (0.035")	1.1 mm (0.045")
Adhesive (nominal thickness as supplied)	1.1 mm (0.045")	1.4 mm (0.055")	1.5 mm (0.060")

\* Actual temperature rating is dependant on specific project requirements and conditions. Please consult your local Canusa representative.

Since 1967, Canusa-CPS has been a leading developer and manufacturer of specialty pipeline coatings for the sealing and corrosion protection of pipeline joints and other substrates. Canusa-CPS high performance products are manufactured to the highest quality standards and are available in a number of configurations to accommodate many specific project applications.

The product information shown here is intended as a guide for standard products.

Consult your Canusa representative for specific projects or unique applications.



### Canusa-CPS A division of ShawCor Ltd.

#### Head Office

25 Bethridge Rd.  
Toronto, ON M9W 1M7 Canada  
Tel: +1 416 743 7111  
Fax: +1 416 743 5927

#### Canada

Suite 3200, 450 - 1st Street S.W.  
Calgary, AB T2P 5H1 Canada  
Tel: +1 403 218 8207  
Fax: +1 403 264 3649

#### Americas

2408 Timberloch Place, Building C-8  
The Woodlands, TX 77380 USA  
Tel: +1 281 367 8866  
Fax: +1 281 367 4304

#### Europe & Middle East

Unit 3, Sterling Park,  
Gatwick Road, Crawley, West Sussex  
RH10 9QT United Kingdom  
Tel: +44 1293 541254  
Fax: +44 1293 541777

#### Asia-Pacific

101 Thomson Road,  
#11-03 United Square  
307591 Singapore  
Tel: +65 6749 8918  
Fax: +65 6749 8919

### Canusa-CPS is registered to ISO 9001:2008

Canusa warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the product data sheet when used in compliance with Canusa's written instructions. Since many installation factors are beyond our control, the user shall determine the suitability of the products for the intended use and assume all risks and liabilities in connection therewith. Canusa's liability is stated in the standard terms and conditions of sale. Canusa makes no other warranty either expressed or implied. All information contained in this data sheet is to be used as a guide and is subject to change without notice. This data sheet supersedes all previous data sheets on this product. E&OE

PDS\_GTSP65\_rev014