

SuperSeal™

Heat shrinkable sleeve for protection of pre-insulated pipe joints

SuperSeal™ is a high performance, heat shrinkable product intended for sealing of pre-insulated pipe joints. SuperSeal™ provides superior barrier against moisture ingress while protecting the joints from the soil stresses associated with Pre-Insulated Pipelines.

Specifically designed for bonding to polyethylene pipes and casings, SuperSeal™ offers low substrate pre-heat temperature thus making the installation of this product simple, forgiving, and most importantly, reliable.

Effective Long Term Sealing

- A combination of cross-linked, Bi-modal HDPE backing with a layer of unique hot melt adhesive, results in a long term barrier impermeable to moisture.
- SuperSeal™ complies with the stringent requirements of the EN 489 standard.

Proven Track Record

- SuperSeal™ has been protecting joints of pre-insulated pipelines for over 25 years

Reliable and Consistent Performance

- Low installation pre-heat temperature ensures forgiving and thus repeatable installation
- High performance backing provides superior mechanical strength required for high stress environments

Flexible Product Options Save Time and Money

- Available in two configurations: pre-cut to specific pipe size and bulk rolls
- Allows for lower inventories of pre-cut sleeves and just-in-time sleeve cutting, thus reducing cost



Applications




Pre-Insulated Pipes



Foam-In-Place



Pre-Foamed Joints



SuperSeal™

Heat shrinkable sleeve for protection of pre-insulated pipe joints

Adhesive Properties	Test Method	Typical Values
Softening Point	ASTM E28	90°C
Lap Shear @ 23°C	ISO 21809-3	225 N/cm ²
Backing Properties		
Tensile Strength	ASTM D638	26 MPa
Elongation	ASTM D638	600
Hardness	ASTM 2240	60 Shore D
Specific Gravity	ISO 1183	0.94
Sleeve Properties		
Adhesion Strength @ 23°C	ISO 21809-3	100 N/cm
Water Absorption	ASTM D570	0.05 %
Low Temp. Flexibility	ASTM D2671	-30°C
Soil Box & Pressure Vessel Test	EN 489	100 cycles, 30 kPa @ 30°C for 24 h
Thickness	T	L
Backing (nominal thickness as supplied)	0.6 mm	0.9 mm
Adhesive (nominal thickness as supplied)	0.9 mm	1.3 mm



Effective
long term sealing

Over 15 years of
in service sealing

The product information shown here is intended as a guide for standard products.

Consult your Canusa representative for specific projects or unique applications.



Canusa-CPS A division of ShawCor Ltd.

Head Office
25 Bethridge Rd.
Toronto, ON M9W 1M7 Canada
Tel: +1 416 743 7111
Fax: +1 416 743 5927

Canada
Suite 3200, 450 - 1st Street S.W.
Calgary, AB T2P 5H1 Canada
Tel: +1 403 218 8207
Fax: +1 403 264 3649

Americas
3838 N. Sam Houston Pkwy E.
Suite 300
Houston, TX 77032
Tel: +1 281 886 2350
Fax: +1 281 886 2353

Europe, Middle East, Africa & Russia
Unit 3, Sterling Park,
Gatwick Road, Crawley, West Sussex
RH10 9QT United Kingdom
Tel: +44 1293 541254
Fax: +44 1293 541777

Asia-Pacific
101 Thomson Road,
#11-03 United Square
307591 Singapore
Tel: +65 6749 8918
Fax: +65 6749 8919

**Canusa-CPS is registered
to ISO 9001:2008**

Canusa warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the product data sheet when used in compliance with Canusa's written instructions. Since many installation factors are beyond our control, the user shall determine the suitability of the products for the intended use and assume all risks and liabilities in connection therewith. Canusa's liability is stated in the standard terms and conditions of sale. Canusa makes no other warranty either expressed or implied. All information contained in this data sheet is to be used as a guide and is subject to change without notice. This data sheet supersedes all previous data sheets on this product. E&OE

PDS_SuperSeal_rev019

Since 1967, Canusa-CPS has been a leading developer and manufacturer of specialty pipeline coatings for the sealing and corrosion protection of pipeline joints and other substrates. Canusa-CPS high performance products are manufactured to the highest quality standards and are available in a number of configurations to accommodate many specific project applications.