

SS80, SS4044P, SS4004P & SS4179 construction sealant primers

Product Description

GE construction primers help promote strong and consistent adhesion of GE branded construction sealants to surfaces that may be difficult to bond to. These primers are supplied ready-to-use (*i.e.*, no mixing required) and easily applied to clean, dry, frost-free, sound surfaces just prior to sealant installation.

Typical Performance Properties

- **SS4044P Primer** - Candidate for adhesion promotion on: anodized & painted aluminum, mill & conversion-coated aluminum, metals & galvanized metals, copper, brass, painted & stainless steel, brick, concrete, stone, terra cotta, unglazed ceramics, plastics and wood. May prove useful on other items as well.
- **SS4004P Primer** - Identical formulation to: SS4044P except tinted pink for confirmation of coverage on light-colored substrates. SS4044P & SS4004P may be used interchangeably.
- **SS4179 Primer** - Candidate for adhesion promotion on: various factory applied paints including; fluoropolymer, acrylics, alkyds, powder coats, etc., most plastics, conversion-coated & painted aluminum, copper and brass. SS4179 is also effective on some porous substrates. SS4179 primer may be suitable for some food contact applications where FDA regulations apply. Determination of specific requirements is recommended prior to use.
- **SS80 Primer** - Candidate for adhesion promotion on all substrates similar to SS4044 but also polyolefin materials such as polypropylene, polyethylene and chlorinated polyethylene, which are normally difficult-to-bond substrates.

- **Short Dry Time** - Most typical applications require only a few minutes of drying time prior to application of the sealant (drying time is variable and dependent upon local conditions at point of use). See typical properties table for drying times.
- **Product Versatility** - These silicone primer solutions are compatible with all GE branded construction silicone products lines. Consult Technical Services for specific sealant-primer-substrate recommendations or testing.

Basic Uses

- GE construction primers enhance adhesion of GE construction products to difficult-to-bond surfaces and substrates.

Packaging

SS4044P, SS4004P & SS4179 are available in 16.0 fl. oz. (473 ml) pint-sized containers, 6 bottles per carton. They are also available in 1 gallon (3.79 L) pail containers. SS80 is available in 300 ml (10.1 fl. oz.) containers, 10 containers per carton.

Limitations

- SS80, SS4044P & SS4004P primers are not recommended for use in food contact applications.
- Not recommended for use on wet, damp, frozen or contaminated surfaces.
- Not recommended to be applied to paints or plastic materials that are adversely effected by the solvents in the primer. Trial applications are recommended to verify chemical compatibility with surfaces.

GE is a registered trademark of General Electric Company and is under license by Momentive Performance Materials Inc. Momentive Performance Materials provides versatile materials as the starting point for its creative approach to ideas that help enable new developments across hundreds of industrial and consumer applications. We are helping customers solve product, process, and performance problems; our silanes, fluids, elastomers, sealants, resins, adhesives, urethane additives, and other specialty products are delivering innovation in everything from car engines to biomedical devices. From helping to develop safer tires and keeping electronics cooler, to improving the feel of lipstick and ensuring the reliability of adhesives, our technologies and enabling solutions are at the frontline of innovation.



SS80, SS4044P, SS4004P & SS4179 construction sealant primers

Customer Evaluation

Customers must evaluate Momentive Performance Materials (MPM) products and make their own determination as to fitness of use in their particular applications.

Precautions

- These primers can be visible on substrates if inadvertently over-applied onto adjacent joint surfaces. See application section pertaining to masking.
- Care should be taken with some plastic substrates such as polystyrene, acrylics or polycarbonates, which can become slightly tacky when excessive primer is applied. This can be minimized or eliminated if the primer is applied with a single, continuous stroke.

Technical Services

Additional technical information and literature may be available from MPM. Laboratory facilities and application engineering are available upon request from MPM. Any technical advice furnished by MPM or any representative of MPM concerning any use or application of any sealant is believed to be reliable but MPM makes no warranty, expressed or implied, of suitability for use in any application for which such advice is furnished.

Specifications

Typical property values of these primers as supplied as set forth in the table below. Typical product data values should not be used as specifications.

Typical Properties - Supplied⁽¹⁾

Property	SS80	SS4004P	SS4044P	SS4179
Color	Clear/ Amber	Pink	Clear/ Amber	Clear/ Colorless
Dry Time; ⁽²⁾ colder environment, minutes	5-20	5-15	5-15	5-10
Dry Time; ⁽²⁾ warmer environment, minutes	3-5	3-5	3-5	3-5
Solids Content, %	8	15	15	6
Specific Gravity	0.88	0.80	0.80	0.91
VOC, ⁽³⁾ g/L	809	636	624	859

(1) Typical value. Actual value may vary.

(2) Drying times shown are typical, however, these times may be longer or shorter depending upon local conditions at point of use. It is suggested to confirm that the primer is dry to the touch prior to application of the sealant.

(3) Excluding water & exempts

Suggested References

In addition to the guidelines provided on this datasheet, MPM recommends that designers and users of GE construction primers familiarize themselves with the latest editions of following industry guidelines and best practices as it relates to priming:

- 1) ASTM C1193 Standard Guide for Use of Joint Sealants.
- 2) ASTM C1481 Standard Guide for Use of Joint Sealants with Exterior Insulation & Finish Systems (EIFS).
- 3) ASTM C1401 Standard Guide for Structural Sealant Glazing
- 4) SWR Institute's Applying Liquid Sealants Applicator Training Program.

Installation

- **CAUTION:** Primers contain solvents. When handling primer, refer to product specific MSDS for information on handling, safety and personal protective equipment.
- **IMPORTANT:** In all cases, the acceptability of each sealant-primer-substrate combination must be confirmed with a lab or site adhesion test prior to proceeding with project installation. MPM can provide lab and field adhesion testing information and suggestions to user upon request.

Surface Preparation

- See specific sealant product datasheets for surface preparation guidelines for use in conjunction with these primers.
- NOTE: THE USE OF A PRIMER IS NOT TO BE MISTAKEN AS A SUBSTITUTE FOR SURFACE PREPARATION.

Primer Application

- The typical application method for these primers is by brushing or wiping. Spraying or dipping of parts is also possible although these two methods sometimes produce erratic results and non-uniform applications (which may not produce uniform adhesion). A single thin uniform application of primer usually provides the strongest bond. Care should be taken so as not to slather or excessively apply the primer onto substrates such that drips or build-ups occur as this can produce poor or inconsistent adhesion.
- For solid smooth substrates (plastics, metals, etc.) a wipe application is suggested. When wiping, apply a thin film of primer to the surface with a clean lint-free cloth or other appropriate wiping material. The application should be in one continuous uniform stroke. Change to a clean rag frequently as contaminants build up or rag becomes dirty.
- For porous and irregular materials (concrete, rough brick, non-smooth stone, etc.) a brush application is suggested. When brushing, it is suggested to use only natural bristle brushes as these are known to provide sufficient results. Brushes with synthetic bristles should be avoided. Synthetic bristles could become dissolved by the primer solvent and possibly affect adhesion.
- On irregular porous surfaces, a second coat of primer may be helpful and a site test using 1 coat vs. 2 coats will show which offers the best performance.
- Confine primer application to areas of joint-sealant bond; do not allow spillage or migration onto adjoining surfaces. See section on masking.
- Under most conditions, a drying time of 5-10 minutes is sufficient prior to application of the silicone adhesive sealant. Under colder temperatures drying time may increase somewhat but is rarely longer than 25 minutes. For all of these silicone primers sufficient humidity must be available for proper drying. Lower humidity can result in longer drying times. Field tests are suggested at each job or application site to find drying time under current conditions. Allow at least the current drying time in minutes between coats if a second coat is desired.
- Primers may be left to dry for up to 24 hours before application of the sealant without loss of bonding effects, however, the primed surface should be covered to prevent dirt or contaminant pickup.

SS80, SS4044P, SS4004P & SS4179 construction sealant primers

Masking

The use of masking tape is recommended where appropriate to ensure a neat job and to protect adjoining surfaces from over-application of primer. Primer that has been inadvertently over-applied onto adjacent surfaces can be extremely difficult to remove, especially on rough or porous substrates.

Storage Conditions

- Product should be stored in the original unopened container at 80°F (27°C) or lower. Lower storage temperatures can help maintain product stability.
- It is important to keep the container closed when not in use since prolonged exposure to moisture can result in gel formation or early product degradation.
- A slight white precipitate may form in storage. This should not impair performance of the primer. Do not shake the container prior to use, but carefully decant the clear primer from the top of the container as needed. A laboratory check of adhesion is recommended prior to product use.

Availability

Information on ordering can be obtained by contacting your local distributor or account manager. The Customer Service telephone number is: +1 (877) 943-7325.

Emergency Service

MPM maintains an around-the-clock emergency service for its products. The American Chemistry Council (CHEMTREC) and CareChem24 International also maintain an around-the-clock emergency service for all chemical products:

Location	Momentive Performance Materials Products	All Chemical Products
Mainland U.S., Puerto Rico	518.233.2500	CHEMTREC: 800.424.9300
Alaska, Hawaii	518.233.2500	CHEMTREC: 800.424.9300
Canada	518.233.2500	CHEMTREC: 800.424.9300
Europe	+518.233.2500 (Albanian, Czech, Danish, Dutch, English, Finnish, French, German, Greek, Hungarian, Italian, Lithuanian, Norwegian, Polish, Portuguese, Romanian, Russian, Serbo-Croatian, Slovak, Spanish, Swedish, Turkish, Ukrainian)	+44.(0)208.762.8322 (UK)
Middle East, All countries, except Israel	+518.233.2500	+961.3.487.287 (Lebanon)
Middle East, Israel	+518.233.2500	+44.(0)208.762.8322 (UK)
Latin America, Asia/Pacific, all other locations worldwide	+518.233.2500	CHEMTREC: +1-703.527.3887 (collect)
At sea	Radio U.S. Coast Guard, which can directly contact Momentive Performance Materials at 518.233.2500 or CHEMTREC at 800.424.9300.	

DO NOT WAIT. Phone if in doubt. You will be referred to a specialist for advice.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers considering the use of this product should review the latest Material Safety Data Sheet and label for product safety information, handling instructions, personal protective equipment if necessary, and any special storage conditions required. Material Safety Data Sheets are available at www.ge.com/silicones or, upon request, from any MPM representative. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

CUSTOMER SERVICE CENTERS

North America

E cs-na.silicones@momentive.com

- | | | |
|---|--------------------------|--------------------------|
| • Specialty Fluids | T +1.800.523.5862 | F +1.304.746.1654 |
| • UA, Silanes and Specialty Coatings | T +1.800.334.4674 | F +1.304.746.1623 |
| • RTVs and Elastomers | T +1.800.332.3390 | F +1.304.746.1623 |
| • Consumer Sealants & Construction Sealants and Adhesives | T +1.877.943.7325 | F +1.304.746.1654 |

Latin America

E cs-la.silicones@momentive.com

- | | | |
|--|---------------------------|---------------------------|
| • Argentina & Chile | T +54.11.4862.9544 | F +54.11.4862.9544 |
| • Brazil | T +55.11.4534.9650 | F +55.11.4534.9660 |
| • Mexico & Central America | T +52.55.2169.7670 | F +52.55.2169.7699 |
| • Venezuela, Ecuador, Peru
Colombia & Caribbean | T +58.212.285.2149 | F +58.212.285.2149 |

Europe, Middle East, Africa and India

E cs-eur.silicones@momentive.com

T 00.800.4321.1000

Pacific

E cs-ap.silicones@momentive.com

T +1.800.820.0202
F +81.276.31.6259
T +0.81.276.20.6182

Worldwide Hotline

T +1.607.786.8131
F +1.607.786.8309
T +1.800.295.2392

Visit us at www.ge.com/silicones

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS GmbH, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS CORRESPOND TO THE RECOMMENDED CONDITIONS OF USE AND/OR OF INCORPORATION AS DESCRIBED BY SUPPLIER IN ITS PRODUCT DATA SHEET AND/OR PRODUCT SPECIFICATIONS. EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.